



FIRE Retardants Inc.™

The Decision You Make May Save A Life!

123 Columbia Court North • Suite 201 • Chaska, MN 55318

952-448-7377 • FAX: 952-448-2613

Fire Retardant "HOT LINE" 1-800-913-9385

e-mail: info@fireretardantsinc.com

Visit Our Web Site at www.fireretardantsinc.com

BURN BARRIER™ NO. 133A

A Water Base Varnish

Fire Retardant Polyurethane Varnish

Fire Hazard Classification, Class "B"

DESCRIPTION:

BURN BARRIER™ No. 133A is a water base, fire retardant polyurethane varnish, with a semi-gloss sheen. It is designated for use on all new or previously coated wood surfaces (except floors). The varnish will not leach or turn white on aging or washing.

RECOMMENDED USES:

For application to all wood surfaces, where a reduction of surface burning characteristics is required to comply with building code requirements.

USED BY:

Schools, Colleges, Nursing Homes, Child Care Centers, Hospitals, Penal Institutions, Apartments, Hotels, Factories, Warehouses, Retail Stores, Restaurants, Utilities, Railroad and other Transportation Companies, Oil and Chemical Installations, Military Installations, and other facilities where fire retardant coatings are required.

PERFORMANCE INFORMATION:

- Class "B" fire rated on wood when applied in two coats at 450 sq.ft./gallon per coat. - See Fire Hazard Classification Section.
- Complies with federal, state, local building and fire code requirements.
- Dries by water evaporation to a tough, flexible, semi-gloss finish.
- Does not leach (lose fire retardancy) on exposure to high humidity.
- Meets all current environmental regulations.
- The coating is somewhat thermoplastic.
- Precaution must be taken when two coated surfaces are touching each other, to prevent sticking and blocking.

CHARACTERISTICS:

Finish Clear

Spreading

Rate . . . 450 sq. ft./gal. (11.0 m²/L)
applied in two coats 3.6
mils wet, 0.9 mils dry per coat

Coverage . . . 225 sq.ft./gal (5.5 m²/L)

V.O.C. Less

Than 0.72 lbs./gal. (86 g/L)

Volume Solids 24% ± 2

Weight Solids 28% ± 2

Drying Time @

77°F & 50% RH:
To touch 15-30 min.
To handle 60 min.
To top coat 30 min.

Type of Cure

. Water Evaporation/Coalescence

Flash Point None

Reducer/Cleaner Water

Shelf Life 6 months (unopened)

Packaging 1 & 5 gal. containers
weight/gal. 8.7 lbs.

Shipping weight 4 gals - 40 lbs.
5 gals - 48 lbs.

Application . . Brush, foam applicator,
conventional and airless spray

PRECAUTIONS:

Surface preparation should be carried out according to good painting practices. All dirt, grease, oil, wax, rust, and other foreign matter must be removed. May be applied to previously coated surfaces in good condition. Glossy surfaces must be dulled with sandpaper or steel wool. All sanding, filling of nail holes, etc. must be completed prior to the application of No. 133A.

Read MSDS before opening containers.

KEEP OUT OF REACH OF CHILDREN

SURFACE PREPARATION:

Surface preparation should be carried out according to good painting practices. All dirt, grease, oil, wax, rust and other foreign matter must be removed.

APPLICATION:

No. 133A can be applied by brush, foam applicator or spray. Stir material well before using, then apply a uniform coat at a coverage rate of 225 sq. ft./U.S. gallon (5.5 m²/L), applied in one coat, or two coats at 450 sq. ft./gal (11.0m²/L). Allow at least 30 minutes drying time between coats. Do not apply when surface or air temperature is below 50°F (10°C).

APPLICATION EQUIPMENT:

Airless Spray
Fluid Pressure 1625 psi
Strainer 100 Mesh
Fluid Hose ¼" diameter
Tip014 - .017



The Decision You Make May Save A Life!

123 Columbia Court North • Suite 201 • Chaska, MN 55318

952-448-7377 • FAX: 952-448-2613

Fire Retardant "HOT LINE" 1-800-913-9385

e-mail: info@fireretardantsinc.com

Visit Our Web Site at www.fireretardantsinc.com

BURN BARRIER™ NO. 133A

A Water Base Varnish

Fire Retardant Polyurethane Varnish

Fire Hazard Classification, Class "B"

FIRE HAZARD CLASSIFICATION

Flame Spread Rating. Class "B" when tested in accordance with ASTM E-84 (NFPA 255, ANSI/UI.723 and UBC 8-1), the coating obtained the following fire hazard classification.

COATING (SYSTEM) DETAILS	CLASSIFICATION OR RATING (WHEN APPLIED TO DOUGLAS FIR)	
	Flame Spread	Smoke Developed
SEALER – Nonc BASE COAT – Type 133A applied at 450 sq. ft./U.S. gal. (11.0 m ² /L) TOP COAT – Type 133A applied at 450 sq. ft./U.S. gal. (11.0 m ² /L)	55	170

As we cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used, we accept no responsibility for results obtained by the application of this information or the safety or suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. We sell the products without warranty or guarantee, and buyers and users assume all responsibility and liability for loss or damage from the handling and use of our products, whether used alone or in combination with other products.