



FIRE Retardants Inc.[™]

The Decision You Make May Save A Life!

123 Columbia Court North • Suite 201 • Chaska, MN 55318

952-448-7377 • FAX: 952-448-2613

Fire Retardant "HOT LINE" 1-800-913-9385

e-mail: info@fireretardantsinc.com

Visit Our Web Site at www.fireretardantsinc.com

Product Information On:

***BURN BARRIER* No. 400 SEMI-GLOSS ACRYLIC CLASS "A" FIRE RESISTANT OVERCOAT COATING**

Product Description:

BURN BARRIER No. 400 Semi-gloss Acrylic is a Class "A" rated, water base, general purpose, fire resistant paint, designed for use on all interior and exterior surfaces, except floors, where maximum durability coupled with fire resistancy is required. No. 400 may be utilized as an overcoat on most intumescent type fire retardant coatings to improve their cleansibility, scrubability, and overall durability.

Surface Preparation:

Surface preparation should be carried out according to good painting practices. Remove all loose, peeling or powdery paint from the surface. All dirt, grease, oil, wax, and other foreign matter **MUST** be removed with a detergent. Rinse surfaces thoroughly with clear water and allow to dry. Repair all cracks, holes, and other surface irregularities. Allow to dry, sand lightly and prime repaired surfaces with No. 400.

New and Previously Painted Surfaces:

BURN BARRIER No. 400 can be applied directly to most surfaces. Metal surfaces must be primed with a good quality metal primer. On combustible surfaces where maximum fire protection is required, a coat of *BURN BARRIER* intumescent fire retardant paint should be applied before the application of *BURN BARRIER* No. 400

Application:

BURN BARRIER No. 400 is ready to use. It can be applied by brush, roller, airless or conventional spray equipment. Stir thoroughly and apply, using a full-bodied coat. If thinning is required, use WATER only, do not exceed ½ pint per gallon. Do not apply when surface or air temperatures are below 50F [10C].

Suggested Coverage Rate:

300 to 420 sq.ft./U.S. gallon [7.4 to 10.3 m²/L depending on substrate.

Drying Time:

Dries to touch in approximately 30 minutes, can be recoated in 1 to 2 hours.



123 Columbia Court North • Suite 201 • Chaska, MN 55318

952-448-7377 • FAX: 952-448-2613

Fire Retardant "HOT LINE" 1-800-913-9385

e-mail: info@fireretardantsinc.com

Visit Our Web Site at www.fireretardantsinc.com

Thinning:

For thinning, use only water [maximum ½ pint per gallon]. For equipment clean up, use warm soapy water.

Tinting:

Available in white, off white, and colors or may be field tinted with most universal tinting colorants.

Packaging:

Standard packaging, 1 gallon, 5 gallon, and 55 gallon containers.

PRECAUTIONS!!

CAUTION! Do not take internally. Close container after each use. **KEEP OUT OF REACH OF CHILDREN.** Protect from freezing.

READ MATERIAL SAFETY DATA SHEET BEFORE OPENING CONTAINERS

Information provided herein is based on information available at the time of printing. However, we make no guarantee or warranty that this product meets or complies with any federal, state, local or foreign government code requirements. As we cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used, we accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. We sell our products without warranty or guarantee, and buyers and users assume all responsibility and liability for loss or damage arising from the use of this information, handling and use of our products, whether used alone or in combination with other products.

Rev. 11/03

© Fire Retardants Inc. All Rights Reserved.